

LUXAFLEX® FABRIC COLLECTION

HARPER

ROLLER BLIND AND PANEL GLIDE SHADE APPLICATIONS



COLOUR RANGE



Glacier



Polish




Papaya



Praline



Evoke



Chaos

Note: Colours are as accurate as the printing process allows

SIMPLY **SMARTER** BY DESIGN

HARPER

ROLLER BLIND AND PANEL GLIDE SHADE APPLICATIONS

FABRIC

Harper is a sophisticated fabric, designed and developed to create a unique 3D geometric pattern.

Available in 6 matching blackout and translucent opacities, Harper's natural colour pallet will complement the style of any room.

FEATURES & BENEFITS

Opacity

6 translucent colours, 6 blackout colours



DURAGUARD® Fabric Protector effectively repels most stain causing agents with its proven, water based, preventative, formula. This fabric protection is totally invisible and has high levels of stain repellence. It makes cleaning and maintaining the fabric much easier.



Treated with Sanitized® Antimicrobial Protection which effectively reduces the development of bacteria, odour and mildew.

Made in Australia

Proudly made in Australia to support the local textile industry.

TECHNICAL SPECIFICATIONS

Composition

100% Polyester

Fabric Weight

Translucent 256 gsm ± 20

Blockout 566 gsm ± 30

Fabric Thickness

Translucent 0.66mm ± 10

Blockout 0.79mm ± 10

Colour Fastness

7 > Blue Scale [AS 2001.4.21]

Roll Size

Translucent 2.8m x 25m, Blockout 2.8 x 20m

Cutting Techniques

Translucent - Ultrasonic

Blockout - Aeronaut

CARE AND CLEANING

General Care:

Dusting with a feather duster is all that is required to keep your fabric looking good.

Stains

For the removal of dirt and grime, simply wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible add a little detergent. Then dry gently with a clean cloth.

COMFORT RATING™# AND SOLAR OPTICAL GUIDE

COMFORT RATING™# GUIDE



SOLAR OPTICAL PROPERTIES (ASTM E 424 -1971)

COLOUR	Heat Properties		Visible Light Properties				UV	Heat Control
	TS	RS	AS	TL	RL	AL	TUV	SC
Papaya Translucent	◆◆◆◆	◆◆◆◆	◆◆◆◆	◆◆◆◆	◆◆◆◆	◆◆◆◆	◆◆◆◆	◆◆◆◆
Papaya Blockout	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆
	40	50	10	35	45	20	10	0.51
	0	64	36	0	54	46	0	0.31

COMFORT RATING™# GUIDE

- ◆ No protection/performance
- ◆◆ Low level of protection/performance
- ◆◆◆ Medium level of protection/performance
- ◆◆◆◆ High level of protection/performance
- ◆◆◆◆◆ Highest level of protection/performance



COMFORT RATING™# GUIDE



COMFORT RATING™ has been devised by Hunter Douglas Limited with the assistance of Canesis Pty Ltd - an Independent Australian Fibre and Textile Research and Development Company.

SOLAR OPTICAL PROPERTIES

AS Heat Absorbance (%)	The percentage of solar energy (heat) absorbed by the fabric. The higher the value the more heat is absorbed by the fabric.
RS Heat Reflectance (%)	The percentage of solar energy (heat) reflected by the fabric. The higher the value the more heat is reflected by the fabric.
TS Heat Transmittance (%)	The percentage of heat transferred through the fabric. The lower the value the less heat is transferred through the fabric.
AL Light Absorbance (%)	The percentage of light absorbed by the fabric. The lower the value the more light is absorbed by the fabric.
RL Light Reflectance (%)	The percentage of light reflected by the fabric. The higher the value the more light is reflected away from the fabric.
TL Light Transmittance (%)	The percentage of light transferred through the fabric. The lower the value the less light is transferred through the fabric.
SC Shading Coefficient	The efficiency of a fabric to provide shade. The higher the figure the more efficient at providing shade.
TUV Ultra Violet Transmittance	The value of ultra violet light going through the fabric. The lower the value the less ultra violet light goes through the fabric.

FIRE RETARDANT INFORMATION



Harper Fabric has a Fire Retardancy rating suitable for residential applications. It has been independently tested to AS1530.3* and AS1530.2^.

Ignitability Index*	0	[Range 0-10]
Spread of Flame Index*	0	[Range 0-10]
Heat Evolved Index*	0	[Range 0-10]
Smoke Developed Index*	8	[Range 0-10]
Flammability Index^	3	[Range 0-100]