

LUXAFLEX® FABRIC COLLECTION

PORTOBELLO

ROLLER BLIND, PANEL GLIDE AND ROMAN SHADE APPLICATIONS



COLOUR RANGE



Blanc



Haze



Pearl



Dove



Smoke



Fog



Cocoa



Mink



Soot



Midnight

Note: Colours are as accurate as the printing process allows

SIMPLY **SMARTER** BY DESIGN



PORTOBELLO

ROLLER BLIND, PANEL GLIDE AND ROMAN SHADE APPLICATIONS

FABRIC

Portobello Fabric expresses elegance with a hint of glamour. The fabric features a modern textured design with a lustrous glow.

Available in matching translucent and blackout alternatives, Portobello fabric can transform a simple room into a luxurious haven.

FEATURES & BENEFITS

Opacity

10 blackout and 10 translucent colours



DURAGUARD® Fabric Protector effectively repels most stain causing agents with it's proven, water based, preventative formula. This fabric protection is totally invisible and has high levels of stain repellence. It makes cleaning and maintaining the fabric much easier.



Treated with Sanitized® Antimicrobial Protection which effectively reduces the development of bacteria, odour and mildew.

Made in Australia

Proudly made in Australia to support the local textile industry.

TECHNICAL SPECIFICATIONS

Composition

100% Polyester

Fabric Weight

Translucent 204gsm ± 30gsm
Blockout 465gsm ± 30gsm

Fabric Thickness

Translucent 0.40mm ± 0.10mm
Blockout 0.70mm ± 0.10mm

Colour Fastness

6-7 Blue Scale

Roll Size

Translucent 2.8m x 25m Blockout 2.8m x 20m

Cutting Techniques

Ultrasonic, Aeronaut

CARE AND CLEANING

General Care:

Dusting with a feather duster is all that is required to keep your fabric looking good.

Stains

For the removal of dirt and grime, simply wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible add a little detergent. Then dry gently with a clean cloth.

COMFORT RATING™# AND SOLAR OPTICAL GUIDE

COMFORT RATING™# GUIDE	SOLAR OPTICAL PROPERTIES (ASTM E 424 -1971)											
	Heat Properties			Visible Light Properties			UV	Heat Control				
COLOUR	TS	RS	AS	TL	RL	AL	TUV	SC				
Midnight Translucent	◆◆◆	◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	18	23	59	1	2	97	2	0.64
Coco Translucent	◆◆◆	◆◆◆◆	◆◆◆◆◆	◆◆◆◆◆	17	22	61	5	5	90	2	0.64
Coco Blockout	◆◆◆	◆◆◆◆◆	BLOCKOUT	◆◆◆◆◆	0	16	84	0	5	95	0	0.64
Midnight Blockout	◆◆◆	◆◆◆◆◆	BLOCKOUT	◆◆◆◆◆	0	17	83	0	4	96	0	0.61

COMFORT RATING™# GUIDE

- ◆ No protection/performance
- ◆◆ Low level of protection/performance
- ◆◆◆ Medium level of protection/performance
- ◆◆◆◆ High level of protection/performance
- ◆◆◆◆◆ Highest level of protection/performance



Heat Protection



UV Protection



Glare Reduction



Shade Factor

COMFORT RATING™# GUIDE



COMFORT RATING™# has been devised by Hunter Douglas Limited with the assistance of Canesis Pty Ltd - an Independent Australian Fibre and Textile Research and Development Company.

SOLAR OPTICAL PROPERTIES

AS Heat Absorbance (%)	The percentage of solar energy (heat) absorbed by the fabric. The higher the value the more heat is absorbed by the fabric.
RS Heat Reflectance (%)	The percentage of solar energy (heat) reflected by the fabric. The higher the value the more heat is reflected by the fabric.
TS Heat Transmittance (%)	The percentage of heat transferred through the fabric. The lower the value the less heat is transferred through the fabric.
AL Light Absorbance (%)	The percentage of light absorbed by the fabric. The lower the value the more light is absorbed by the fabric.
RL Light Reflectance (%)	The percentage of light reflected by the fabric. The higher the value the more light is reflected away from the fabric.
TL Light Transmittance (%)	The percentage of light transferred through the fabric. The lower the value the less light is transferred through the fabric.
SC Shading Coefficient	The efficiency of a fabric to provide shade. The higher the figure the more efficient at providing shade.
TUV Ultra Violet Transmittance	The value of ultra violet light going through the fabric. The lower the value the less ultra violet light goes through the fabric.

FIRE RETARDANT INFORMATION



Portobello Fabric has a Fire Retardancy rating suitable for residential applications. It has been independently tested to AS1530.3* and AS1530.2^.

Blockout

Ignitability Index*	9	[Range 0-10]
Spread of Flame Index*	0	[Range 0-10]
Heat Evolved Index*	0	[Range 0-10]
Smoke Developed Index*	6	[Range 0-10]
Flammability Index^	5	[Range 0-100]

Translucent

Ignitability Index*	0	[Range 0-10]
Spread of Flame Index*	0	[Range 0-10]
Heat Evolved Index*	0	[Range 0-10]
Smoke Developed Index*	0	[Range 0-10]
Flammability Index^	49	[Range 0-100]